

G11-450-02

Lithology	Sample No.	Sample	From m	To m	Interval m	Zn ppm	Pb ppm	Ag ppm	Au ppb	Ba ppm	Ni ppm	Cu ppm	Mo ppm	Sb ppm	Sn ppm	W ppm	Bi ppm	Cd ppm	As ppm	S ppm	Rb ppm	Fe ppm	Mn ppm	Ca ppm	Mg ppm	Al ppm	K ppm	Na ppm	Si ppm	Be ppm	Ce ppm	Co ppm	Cr ppm	Cs ppm	Ga ppm	Ge ppm	Hf ppm	In ppm	La ppm	Li ppm	Nb ppm	P ppm	Re ppm	Sc ppm	Se ppm	Sr ppm	Ta ppm	Te ppm	Th ppm	Ti ppm	Tl ppm	U ppm	V ppm	Y ppm	Zr ppm
Volc clastic	101252	1/2 CORE	204.00	204.20	0.20	47	44	0.09	<1	80	11	23	11.9	2.2	1.1	0.6	0.02	0.2	29.3	10.0	6.9	30.0	231	1.4	0.6	2.8	0.3	0.6	12.8	0.94	32.9	9.2	17.0	0.5	10.6	0.6	2.5	0.06	13.3	18.3	24.3	1310	0.002	5.5	1.0	86	1.6	-0.05	2.2	0.59	0.81	0.7	42	10.1	123.5
Volc clastic	100724	1/2 CORE	204.20	204.80	0.60	23	29	0.03		200	11	16	8.0	1.7	1.5	0.8	0.01	0.1	19.9	10.0	26.5	21.7	167	1.4	0.5	4.7	1.0	3.1	17.1	1.45	75.9	13.3	21.0	1.7	14.8	0.2	4.7	0.08	30.2	11.9	42.0	2470	0.002	10.4	2.0	119	2.8	-0.05	3.5	1.01	0.40	1.3	63	21.2	222.0
Volc clastic	100725	1/2 CORE	204.80	205.20	0.40	19	20	0.00		260	14	13	7.0	1.4	1.9	1.1	0.02	0.1	13.3	10.0	38.5	15.6	153	1.7	0.4	6.6	1.5	2.1	20.0	1.92	106.0	16.6	34.0	2.6	20.0	0.2	5.6	0.09	43.9	8.3	68.2	3710	0.001	14.0	1.0	172	3.8	-0.05	4.4	1.40	0.26	1.6	87	31.1	311.0
Volc clastic	100726	1/2 CORE	205.20	205.70	0.50	16	21	0.00		330	15	13	5.9	1.7	2.4	1.1	0.02	0.1	14.5	10.0	48.3	12.7	113	1.5	0.4	7.7	1.9	2.3	21.5	2.51	141.5	17.2	29.0	3.3	24.3	0.3	7.2	0.11	59.8	8.1	81.6	3940	0.001	16.2	1.0	212	4.8	-0.05	5.5	1.53	0.26	2.0	91	37.0	378.0
Volc clastic	100727	1/2 CORE	205.70	206.50	0.80	15	22	0.00		420	17	12	5.7	1.9	3.3	0.9	0.04	0.1	19.3	10.0	58.0	10.2	98	1.2	0.5	8.5	2.4	2.0	22.9	2.82	177.0	18.1	22.0	3.5	27.4	0.3	8.7	0.13	73.4	7.9	104.5	3250	0.001	15.6	2.0	234	6.1	-0.05	7.7	1.31	0.29	1.7	58	33.8	451.0
Volc clastic	101254	1/2 CORE	211.00	211.15	0.15	20	58	0.04	<1	300	101	26	22.2	7.6	0.5	0.1	0.02	1.6	27.8	10.0	27.7	33.9	429	2.2	0.2	0.8	0.1	0.1	9.2	16.7	141.3	14.0	0.2	3.2	0.1	0.4	0.05	6.5	10.7	4.0	310	0.002	2.6	2.0	99	0.3	-0.05	0.4	1.12	2.01	0.3	17	6.5	18.6	
Volc clastic	100717	1/2 CORE	212.00	212.50	0.50	23	27	0.01		480	57	19	10.2	4.2	3.4	1.0	0.06	0.2	77.8	6.6	67.9	6.8	161	1.4	0.6	8.5	2.6	1.5	22.6	3.58	181.0	52.3	55.0	4.2	27.3	0.2	8.4	0.10	78.8	9.5	88.3	4240	0.003	18.1	1.0	184	5.7	-0.05	7.5	1.98	0.50	4.8	176	40.0	352.0
Volc clastic	100718	1/2 CORE	212.50	213.25	0.75	22	39	0.07		450	53	23	7.7	4.6	3.1	1.1	0.05	0.2	24.9	10.0	58.4	15.6	164	1.6	0.5	7.3	2.4	0.9	20.5	3.21	68.0	41.5	51.0	4.0	24.0	0.2	6.3	0.09	24.4	8.4	77.6	3910	0.002	17.1	1.0	125	4.6	-0.05	5.3	1.86	0.47	2.3	158	36.0	295.0
Volc clastic	100719	1/2 CORE	213.25	213.50	0.25	23	56	0.57		440	49	37	11.6	6.9	2.1	0.9	0.02	0.6	40.7	10.0	43.7	22.0	452	3.3	0.5	5.2	1.6	0.6	14.7	2.08	65.1	30.2	41.0	2.8	16.7	0.2	4.7	0.09	24.6	8.2	46.9	3140	0.002	12.0	1.0	151	3.0	-0.05	3.4	1.32	0.96	2.5	110	33.8	205.0
Volc clastic	100723	1/2 CORE	213.50	214.00	0.50	34	26	0.23		300	81	25	7.1	4.1	4.1	1.8	0.05	0.1	23.1	6.4	74.9	7.0	137	1.6	0.7	8.9	3.1	1.3	19.1	4.52	88.9	54.9	67.0	5.0	32.7	0.2	10.1	0.13	36.4	15.2	104.0	4980	0.003	18.4	2.0	162	6.5	-0.05	6.6	2.60	0.47	7.6	220	50.8	416.0
chert	101251	1/2 CORE	226.85	227.00	0.15	15	25	0.13		130	68	22	2.1	1.5	0.9	0.3	0.06	0.1	16.5	5.1	16.4	5.8	292	1.8	0.4	1.7	0.5	0.1	36.5	0.75	19.0	12.9	52.0	0.9	5.0	0.1	2.2	0.03	9.7	9.5	18.8	780	0.014	7.1	2.0	59	1.2	-0.05	2.8	0.50	0.21	5.7	60	23.0	85.9
Arg Lmst	100721	1/2 CORE	257.30	257.50	0.20	40	56	0.26		230	109	41	16.7	3.3	1.7	0.8	0.30	0.1	30.3	10.0	84.4	13.0	368	9.2	0.7	4.1	1.8	0.1	18.1	2.69	43.0	13.9	124.0	5.5	13.3	0.6	3.3	0.4	29.5	0.17	10.3	390	0.291	23.5	7.0	128	0.6	-0.05	10.8	0.22	1.36	59.6	212	63.6	120.5
chert	100722	1/2 CORE	260.00	260.30	0.30	22	42	0.22		140	82	49	16.1	2.4	1.0	0.4	0.15	0.6	21.6	10.0	39.3	17.1	147	0.2	0.2	2.3	0.9	0.1	29.9	1.23	14.5	10.7	66.0	2.4	6.3	0.1	1.8	0.03	8.6	12.0	4.6	70	0.174	6.5	5.0	21	0.3	-0.05	4.6	0.11	0.81	2.6	111	11.9	57.7
lmst brx	101253	1/2 CORE	301.30	301.50	0.20	17	11	0.05		80	28	10	1.5	0.6	0.5	0.3	0.07	0.3	4.8	1.8	21.7	1.9	353	30.5	0.4	1.2	0.6	0.0	8.2	1.01	20.4	4.7	23.0	1.5	3.2	0.1	0.9	0.01	14.6	4.8	3.0	150	0.011	3.0	1.0	193	0.2	-0.05	2.7	0.07	0.20	3.3	27	26.0	30.9
chert	100058	1/2 CORE	305.70	306.80	1.10	791	24	0.06		290	102	32	11.0	1.1	2.4	1.5	0.25	9.6	11.6	6.0	60.5	6.2	146	1.1	0.3	3.6	1.6	0.1	34.9	2.70	114.5	20.9	69.0	3.9	10.8	0.3	4.1	0.05	85.2	17.8	11.3	430	0.014	13.1	1.0	63	1.0	0.08	10.6	1.6	0.69	9.2	75	56.6	116.5
chert	101250	1/2 CORE	306.80	307.00	0.20	388	47	0.20	2	70	295	62	42.5	2.7	2.8	2.6	0.33	5.8	29.7	10.0	86.8	11.8	155	0.5	0.5	4.9	2.1	0.1	28.5	3.91	185.5	43.2	83.0	5.6	14.9	0.5	4.1	0.08	125.5	23.0	18.6	1250	0.038	15.8	3.0	87	1.1	0.14	12.4	0.27	1.43	19.2	119	55.7	133.5
chert	100057	1/2 CORE	307.00	307.40	0.40	425	38	0.04		350	312	57	26.7	2.6	3.6	3.0	0.41	6.7	33.4	8.8	108.0	9.3	377	5.0	1.0	6.3	2.7	0.1	21.2	4.01	187.5	69.9	81.0	6.5	20.0	0.4	6.7	0.08	130.0	21.9	27.8	690	0.023	20.1	2.0	154	1.7	0.19	15.8	3.0	1.41	14.8	117	101.0	197.0
chert	100728	1/2 CORE	315.00	315.40	0.40	311	6	0.14		60	31	10	2.6	0.5	0.9	0.6	0.09	3.0	5.0	2.2	13.7	3.2	193	1.5	0.3	1.0	0.4	0.1	44.2	4.02	20.6	4.4	30.0	0.8	2.8	0.1	0.6	0.01	13.9	4.3	2.0	150	0.025	2.6	2.0	51	0.3	-0.05	2.0	0.04	0.28	6.1	32	18.8	19.0
chert	100729	1/2 CORE	320.05	320.63	0.58	162	8	0.09		110	52	16	4.0	0.8	1.3	0.7	0.09	1.7	5.4	1.8	28.1	2.7	151	0.7	0.2	2.0	0.9	0.1	44.7	0.78	55.8	8.8	47.0	1.3	6.4	0.1	1.9	0.02	43.5	8.7	7.7	320	0.027	5.0	2.0	50	0.5	-0.05	3.6	0.1	0.45	6.7	49	23.5	50.7
lmst brx	101255	1/2 CORE	350.90	351.80	0.90	185	11	0.05		70	33	11	4.4	0.5	1.0	0.05	0.2	3.6	2.2	27.0	2.0	213	22.0	0.5	0.2	1.0	0.5	0.2	12.8	0.58	37.0	7.5	17.0	2.0	6.3	0.1	2.0	0.03	24.4	6.0	18.9	470	0.011	3.7	1.0	169	1.1	0.05	3.0	0.2	0.51	3.5	30	19.6	64.0
lmst brx	101256	1/2 CORE	351.80	352.80	1.00	29	4	0.03		60	25	10	4.0	0.3	1.1	1.5	0.08	0.5	3.3	1.7	25.4	1.8	185	17.6	0.5	2.0	0.9	0.0	14.9	0.58	38.4	6.8	17.0	2.1	6.1	0.1	2.0	0.03	20.8	7.0	16.3	560	0.008	3.9	1.0	153	1.1	-0.05	3.0	0.24	0.27	3.1	31	18.7	61.1
lmst brx	101257	1/2 CORE	352.80	353.80	1.00	21	10	0.03		100	38	23	4.5	2.5	2.4	1.5	0.08	0.5	9.0	8.0	43.1	7.8	171	9.6	0.4	4.8	2.8	0.0	17.0	0.86	53.9	21.1	43.0	4.4	16.8	0.2	4.7	0.06	25.7	6.1	51.0	2340	0.007	5.4	1.0	98	2.8	-0.05	3.6	1.18	0.59	2.8	95	22.5	175.5
lmst brx	101258	1/2 CORE	353.80																																																				

WL_Imst	100074	1/2 CORE	409.30	410.20	0.90	11	4	0.03	10	18	5	4.0	0.7	0.2	0.3	0.02	0.3	4.1	0.2	9.2	0.4	132	36.4	0.7	0.5	0.3	0.0	0.9	0.37	5.9	3.9	4.0	0.5	1.2	0.1	0.3	0.01	4.1	2.0	0.9	60	0.009	1.2	1.0	174	0.1	<0.05	0.7	0.03	0.13	0.5	10	5.8	8.6
WL_Imst	100075	1/2 CORE	410.20	411.10	0.90	9	3	0.02	10	13	4	2.6	0.5	0.1	0.2	0.02	0.3	3.1	0.2	6.0	0.3	151	35.7	0.5	0.3	0.2	0.0	0.6	0.29	5.5	3.1	3.0	0.3	0.8	0.1	0.2	0.01	3.9	1.4	0.6	70	0.009	0.9	1.0	152	0.0	<0.05	0.5	0.02	0.06	0.9	7	7.1	9.1
WL_Imst	100076	1/2 CORE	411.10	412.00	0.90	11	3	0.02	10	13	4	3.1	0.5	0.1	0.1	0.01	0.3	2.9	0.2	4.9	0.2	81	35.4	0.4	0.3	0.1	0.0	0.1	0.24	3.4	2.5	3.0	0.3	0.7	0.1	0.2	0.01	2.8	1.3	0.5	80	0.004	0.7	1.0	141	0.0	<0.05	0.4	0.01	0.08	0.6	6	4.9	6.9
WL_Imst	100077	1/2 CORE	412.00	413.00	1.00	12	4	0.02	10	15	5	3.4	0.6	0.1	0.1	0.02	0.3	3.2	0.2	5.5	0.3	99	36.4	0.5	0.3	0.2	0.0	0.1	0.26	3.5	2.9	3.0	0.3	0.7	0.1	0.2	0.01	3.1	1.4	0.7	90	0.008	0.7	1.0	154	0.0	<0.05	0.4	0.02	0.12	0.7	7	5.8	10.9
WL_Imst	100078	1/2 CORE	413.00	413.90	0.90	16	5	0.02	20	15	6	4.6	0.7	0.1	0.1	0.02	0.3	3.6	0.2	5.1	0.3	92	36.3	0.7	0.3	0.1	0.0	0.5	0.24	3.6	2.9	2.0	0.3	0.7	0.1	0.2	0.01	2.4	1.3	0.5	60	0.006	0.8	1.0	173	0.0	<0.05	0.3	0.01	0.08	0.6	7	6.1	7.6
WL_Imst	100079	1/2 CORE	413.90	414.90	1.00	14	4	0.02	10	11	5	1.8	0.5	0.1	0.1	0.01	0.4	2.2	0.2	4.1	0.2	88	37.2	0.5	0.2	0.1	0.0	0.1	0.19	3.1	2.1	2.0	0.2	0.5	0.1	0.2	0.01	2.8	1.1	0.4	70	0.003	0.6	1.0	192	0.0	<0.05	0.3	0.01	0.06	0.4	5	5.1	7.7
WL_Imst	100081	1/2 CORE	414.90	415.90	1.00	13	4	0.02	10	13	6	2.3	0.7	0.1	0.1	0.02	0.4	2.9	0.2	6.4	0.4	154	34.8	0.8	0.3	0.2	0.0	0.6	0.26	4.3	2.6	3.0	0.3	0.9	0.1	0.2	0.01	3.5	1.4	0.6	60	0.002	0.9	0.1	182	0.0	<0.05	0.5	0.02	0.09	0.4	7	7.2	6.7
WL_Imst	100082	1/2 CORE	415.90	416.80	0.90	10	4	0.03	10	16	6	2.8	0.7	0.1	0.2	0.02	0.3	3.9	0.3	7.0	0.4	137	35.1	0.7	0.4	0.2	0.0	0.5	0.28	4.1	3.7	3.0	0.3	0.9	0.1	0.3	0.01	3.2	1.5	0.7	70	0.003	1.0	0.1	176	0.1	<0.05	0.6	0.02	0.12	0.5	7	6.6	9.0
WL_Imst	100083	1/2 CORE	416.80	417.70	0.90	16	3	0.01	10	11	4	1.7	0.4	0.1	0.1	0.01	0.3	2.7	0.2	3.9	0.3	176	37.3	0.7	0.2	0.1	0.0	0.1	0.20	4.3	2.4	3.0	0.2	0.6	0.1	0.2	0.01	2.9	0.9	0.4	90	0.002	0.6	1.0	210	0.0	<0.05	0.3	0.01	0.07	0.5	5	5.1	8.6
WL_Imst	100084	1/2 CORE	417.70	418.60	0.90	15	8	0.03	10	31	8	6.7	1.1	0.2	0.3	0.03	0.4	6.8	0.8	11.5	0.9	259	35.1	1.3	0.6	0.3	0.0	1.0	0.34	5.7	6.4	5.0	0.5	1.5	0.1	0.4	0.01	3.5	1.9	1.2	130	0.007	1.2	1.0	162	0.1	<0.05	0.8	0.03	0.18	0.4	10	5.0	10.6
WL_Imst	100085	1/2 CORE	418.60	419.50	0.90	14	6	0.03	10	20	5	5.4	0.7	0.2	0.2	0.02	0.4	4.5	0.8	6.9	1.0	274	34.9	1.1	0.4	0.2	0.0	0.6	0.27	5.9	4.3	3.0	0.4	0.9	0.1	0.3	0.03	3.7	1.4	0.8	130	0.004	0.8	1.0	145	0.1	<0.05	0.6	0.02	0.14	0.6	7	7.1	11.5
WL_Imst	100086	1/2 CORE	419.50	420.40	0.90	25	13	0.07	20	41	14	33.5	1.6	0.3	0.3	0.04	0.6	10.4	0.7	13.1	0.7	115	35.2	0.6	0.7	0.3	0.0	1.1	0.47	4.7	7.9	6.0	0.7	1.7	0.1	0.4	0.01	3.5	2.5	1.4	280	0.009	1.2	1.0	217	0.1	<0.05	0.9	0.03	0.29	0.6	12	6.3	12.7
WL_Imst	100087	1/2 CORE	420.40	421.30	0.90	28	18	0.16	10	56	16	8.1	1.7	0.3	0.2	0.03	0.6	13.7	2.3	11.4	2.1	158	33.6	0.7	0.6	0.3	0.0	1.0	0.40	4.4	6.8	5.0	0.6	1.4	0.1	0.4	0.01	3.0	2.2	1.6	350	0.007	1.0	1.0	181	0.1	<0.05	0.9	0.03	0.26	0.5	9	5.9	12.2
WL_Imst	100088	1/2 CORE	421.30	422.20	0.90	28	9	0.09	10	22	15	3.5	0.9	0.2	0.1	0.03	0.4	6.7	1.5	4.5	1.4	140	35.7	0.6	0.2	0.1	0.0	0.1	0.17	3.4	3.7	3.0	0.2	0.6	0.1	0.2	0.01	2.6	1.0	0.6	220	0.004	0.6	1.0	183	0.0	<0.05	0.4	0.01	0.12	0.4	4	6.0	7.8
WL_Imst	100089	1/2 CORE	422.20	423.20	1.00	18	3	0.07	10	9	14	0.8	0.3	0.1	0.1	0.01	0.4	2.6	0.1	3.2	0.2	148	36.7	0.6	0.2	0.1	0.0	0.1	0.16	3.3	1.6	2.0	0.1	0.5	0.1	0.2	0.01	2.8	0.8	0.3	200	0.002	0.7	1.0	194	0.0	<0.05	0.2	0.01	0.04	0.7	3	6.7	8.5
WL_Imst	100090	1/2 CORE	423.20	424.10	0.90	13	2	0.03	10	6	8	0.5	0.2	0.1	0.1	0.01	0.3	1.8	0.1	1.5	0.2	157	37.0	0.7	0.1	0.0	0.0	0.1	0.08	2.9	1.2	1.0	0.1	0.3	0.1	0.1	0.01	2.8	0.6	0.2	150	0.002	0.4	1.0	176	0.0	<0.05	0.1	0.00	0.02	0.7	2	6.0	6.2
WL_Imst	100091	1/2 CORE	424.10	425.10	1.00	18	3	0.02	10	9	5	1.3	0.3	0.1	0.1	0.01	0.4	2.2	0.1	2.7	0.2	131	36.5	0.6	0.1	0.1	0.0	0.1	0.13	3.5	1.7	2.0	0.1	0.4	0.1	0.2	0.01	3.1	0.8	0.4	160	0.004	0.5	1.0	183	0.0	<0.05	0.2	0.01	0.03	0.4	3	6.5	5.9
WL_Imst	100092	1/2 CORE	425.10	426.00	0.90	26	4	0.02	10	16	7	3.3	0.6	0.2	0.1	0.02	0.6	3.1	0.3	5.9	0.3	110	36.1	0.4	0.3	0.1	0.0	0.5	0.25	4.4	2.8	3.0	0.3	0.7	0.1	0.3	0.01	3.5	1.3	1.0	180	0.003	0.8	1.0	171	0.1	<0.05	0.5	0.01	0.10	0.5	5	8.6	9.9
WL_Imst	100093	1/2 CORE	426.00	426.90	0.90	27	4	0.02	10	16	7	1.4	0.6	0.1	0.2	0.02	0.7	2.6	0.4	5.6	0.4	133	37.5	0.4	0.3	0.1	0.0	0.7	0.22	4.3	2.4	3.0	0.3	0.7	0.1	0.2	0.01	3.1	1.2	0.6	220	0.002	0.8	1.0	195	0.0	<0.05	0.4	0.01	0.08	0.4	5	6.6	8.1
WL_Imst	100094	1/2 CORE	426.90	427.90	1.00	8	2	0.01	10	8	3	0.4	0.3	0.1	0.1	0.01	0.2	1.4	0.2	2.3	0.3	211	36.8	0.7	0.1	0.1	0.0	0.1	0.16	3.6	1.5	1.0	0.1	0.3	0.1	0.2	0.03	2.9	0.7	0.2	170	0.002	0.5	1.0	196	0.0	<0.05	0.2	0.01	0.03	0.5	2	5.3	10.2
WL_Imst	100095	1/2 CORE	427.90	428.80	0.90	8	2	0.02	10	9	3	0.6	0.3	0.1	0.1	0.01	0.3	1.3	0.1	3.1	0.2	176	36.3	0.7	0.1	0.1	0.0	0.1	0.16	3.6	1.7	2.0	0.1	0.4	0.1	0.2	0.01	3.0	0.9	0.3	110	0.002	0.6	1.0	161	0.0	<0.05	0.2	0.01	0.04	0.3	3	5.2	9.9
WL_Imst	100096	1/2 CORE	428.80	429.80	1.00	14	3	0.01	10	8	3	0.7	0.4	0.1	0.1	0.01	0.4	1.4	0.1	2.9	0.2	127	36.5	0.3	0.1	0.1	0.0	0.1	0.14	2.9	1.3	2.0	0.1	0.4	0.1	0.1	0.01	2.3	0.8	0.3	90	0.002	0.6	1.0	159	0.0	<0.05	0.2	0.01	0.04	0.3	2	3.7	6.4
WL_Imst	100097	1/2 CORE	429.80	430.70	0.90	34	4	0.01	10	15	6	1.0	0.4	0.1	0.2	0.02	0.8	2.9	0.2	8.0	0.3	98	36.0	0.5	0.4	0.2	0.0	0.8	0.26	6.3	2.6	3.0	0.4	0.9	0.1	0.2	0.01	4.4	2.0	0.6	90	0.002	1.2	1.0	149	0.0	<0.05	0.4	0.02	0.08	0.4	6	5.6	8.3
Ballynash	100098	1/2 CORE	430.70	431.60	0.90	9	4	0.01	20	28	9	0.3	0.2	0.2	0.3	0.03	0.2	8.9	0.2	15.1	0.3	186	35.2	0.3	0.6	0.3	0.0	1.8	0.60	7.4	5.7	4.0	0.7	1.7	0.1	0.3	0.01	4.4	3.6	1.2	140	0.002	1.6	1.0	134	0.1	<0.05	0.8	0.03	0.12	0.4	7	8.1	18.7
Ballynash	100099	1/2 CORE	431.60	432.50	0.90	10	3	0.01	20	30	8	0.2	0.2	0.3	0.2	0.03	0.1	4.8	0.2	15.1	0.4	294	30.2	0.3	0.6	0.3	0.0	5.8	0.49	7.4	5.7	7.0	0.8	1.7	0.1	0.5	0.01	4.0	4.2	1.6	200	0.002	1.5	0.1	110	0.1	<0.05	0.8	0.03	0.12	0.5	7	6.7	19.2
ABL	100100	1/2 CORE	480.00	480.90	0.90	21	16	0.06	50	59	8	0.4	1.2	0.6	0.7	0.07	0.0	33.4	2.1	54.4	2.8	994	17.6	0.9	2.2	1.0	0.0	18.2	3.04	23.1	12.7	24.0	2.2	6.0	0.1	2.3	0.02	12.7	13.8	3.5	340	0.002	4.6	1.0	235	0.2	<0.05	2.9	0.11	0.45	1.2	25	12.1	87.2
ABL	100201	1/2 CORE	480.90	481.90	1.00	16	7	0.04	70	22	7	0.5	0.7	0.9	0.8	0.11	0.0	8.4	0.4	81.0	1.1	669	13.2	1.1	3.1	1.5	0.0	25.5	2.98	35.8	6.4	30.0	2.3	9.7	0.1	6.5	0.04	16.8	15.3	6.8	320	0.002	7.2	1.0	1									